

HORIZONTAL REPAIR

Master Format #: 03 01 30.71

EUCOREPAIR SCC

SELF-CONSOLIDATING CONCRETE REPAIR MORTAR



EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) bags

Code: 088SC 50

Bulk bags suitable for mixing in ready-mix trucks available (MTO)

APPROXIMATE YIELD

50 lb (22.7 kg) unit: 0.375 ft³ (0.01 m³) per unit when mixed with 0.5 gallons (1.9 L) of potable water.

MINIMUM/MAXIMUM APPLICATION THICKNESS

1 inch (2.5 cm) to full depth

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

1 year in original, unopened package

SPECIFICATIONS/COMPLIANCES

- NSF/ANSI/CAN Standard 61

DESCRIPTION

EUCOREPAIR SCC is a versatile, one component, self-consolidating repair mortar that is shrinkage-compensated, polymer and microfiber modified, and contains an integral corrosion inhibitor. It is designed for horizontal and formed vertical/overhead structural repairs in applications from 1 inch (2.5 cm) to full depth.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Shrinkage compensation and reduction to minimize cracking
- Pre-mixed with pea gravel, ready-to-use
- Low permeability with excellent freeze-thaw resistance
- Polymer and microfiber modified
- Interior or exterior use
- Contains an integral corrosion inhibitor
- Long working time

PRIMARY APPLICATIONS

- Parking decks
- Joint repairs
- Balconies
- Equipment bases
- Pavements
- Beams
- Vertical and overhead formed repairs

COMMON METHODS

- Trowelable (horizontal applications)
- Pumpable
- Form and pour

The following coverage rates are approximations based on yield of a 50 lb (22.7 kg) unit mixed at standard consistency.

Application Thickness - inches (mm)	1 (25)	1 1/2 (38)	2 (51)	3 (76)	4 (102)	6 (152)
Coverage Area per Unit - ft ² (m ²)	4.4 (0.41)	2.9 (0.27)	2.2 (0.20)	1.4 (0.13)	1.1 (0.10)	0.7 (0.07)

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C39	Compressive Strength 3" x 6" cylinder @ 0.5 gal/50 lb bag (1.90 L/22.7 kg bag)	1 day 2,750 psi (19 MPa) 3 days 4,100 psi (28 MPa) 7 days 4,800 psi (33 MPa) 28 days 5,600 psi (39 MPa)
ASTM C666 Procedure A	Freeze/Thaw Resistance	300 cycles . . . > 98% relative dynamic modulus
ASTM C1012	Sulfate Resistance	6 months +0.023%
	Surface Resistivity	28 days 31,200 ohm-cm
ASTM C78	Flexural Strength	1 day 450 psi (3.1 MPa) 3 days 800 psi (5.5 MPa) 7 days 900 psi (6.2 MPa)
ASTM C1202	Rapid Chloride Permeability	28 days 1800 coulombs
ASTM C157*	Length Change	28 day shrinkage < 0.050%
ASTM C1611	Slump Flow	Initial 24 - 33 inches (61 to 84 cm) 30 minutes 24 - 33 inches (61 to 84 cm)
ASTM C1621	J-Ring Slump Flow	25 inches (63 cm) Passing Ability: 0.75 inch (1.9 cm) no visible blocking
ASTM C403	Set Time	Initial approximately 9 hours
ASTM C138	Fresh Wet Density	144.4 lb/ft ³ (2,313.1 kg/m ³)
ASTM C882	Slant Shear Bond Strength	7 days 3,401 psi (23.4 MPa) 28 days 3,880 psi (26.8 MPa)
ASTM C1581	Crack Resistance	Net Time Until Cracking . . . 15.5 days Stress Rate 16 psi/day (0.11 MPa/day) Potential for Cracking . . . Moderate-Low

*Based on 50% RH @ 23 °C (73 °F) (3" x 3" x 11" beam specimens were removed from molds @ 24 hours)

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile of at least CSP 5-7 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Substrate shall be saturated surface dry (SSD) without standing water.

Formwork: For building forms, refer to ACI 347R - Guide to Formwork for Concrete. Forms should be filled with water 24 hours prior to placement of EucoRepair SCC to ensure tightness and adequate saturation. Ensure forms are completely drained before pouring of product and any drainage outlets are sealed.

Priming & Bonding (Saw Cut & Chipped Out Repairs, Form & Pour Repairs): Thoroughly clean any exposed reinforcing steel, and apply DURALPREP A.C. to the concrete and the reinforcing steel within the repair area. Refer to the DURALPREP A.C. technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of EUCOREPAIR SCC to the saturated surface dry (SSD) concrete surface may be used for bonding. The repair material must be placed on the scrub coat before the scrub coat dries out.

Mixing: All materials should be in the proper temperature range of 60 °F (15 °C) to 90 °F (32 °C). Single 50 lb (22.7 kg) bags may be mixed with a drill and "jiffy" mixer. Use a horizontal shaft, paddle type mortar mixer for mixing multiple bags simultaneously. Add the appropriate amount of water, 0.45 - 0.50 gal (1.7 - 1.9 L) per bag, for the batch size and then add the dry product. Mix a minimum of 3 minutes. **Mixing Bulk Bags:** Add approximately 80% of the appropriate water for the batch size to the ready-mix concrete truck. Fully open the top of the bulk bag. Position the bulk bag over the truck opening using a forklift or crane. While the drum is turning at slow speed, cut the bottom of the bulk bag to release contents into truck. Use the remaining mix water to wash down any dry, stuck material into the drum. Mix for a minimum of 5 minutes after last bulk bag is added. Reverse drum and check consistency. Note: It is recommended to keep 50 lb (22.7 kg) bags on hand to adjust consistency if needed. The mixed product should be transported to the repair area and placed immediately.

Placement: Pump or pour product immediately after mixing. Vibration is typically not required, but form vibration can be used to ensure proper consolidation in situations which restrict flowability. If vibration is used, do not vibrate in excess as this can lead to segregation of the aggregate. When placing material, refer to ACI 304R - Guide for Measuring, Mixing, Transporting, and Placing Concrete.

Curing and Sealing: Cure exposed surfaces of EUCOREPAIR SCC with a high-solids curing compound from The Euclid Chemical Company. In hot, windy, or direct sunlight situations, re-wet the surface after the curing compound has dried and cover with polyethylene for a minimum of three days. If a curing compound is not desired, wet cure for a minimum of three days.

PRECAUTIONS/LIMITATIONS

- Do not use material at temperatures below 45 °F (7 °C).
- Keep repair from freezing until a minimum strength of 1,000 psi (6.90 MPa) is reached.
- Do not extend with aggregate.
- Do not use as an unbonded topping.
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- If quick turnaround for application of an impermeable coating (such as epoxy) is desired, use EUCOREPAIR SCC FAST instead.
- In all cases, consult the Safety Data Sheet before use.

Rev. 10.23

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.